

## VISCOSITIES of COMMON MATERIALS

---

Material	Temp. Deg. F	Viscosity Centipoise
Water	68	1
Gasoline	70	8
Kerosene	70	10
98% Sulfuric Acid	70	25
SAE 10 Oil	70	60
SAE 30 Oil	70	300
SAE 50 Oil	70	600
SAE 110 Oil	70	2,000
SAE 10 Oil	140	15
SAE 30 Oil	140	30
SAE 50 Oil	140	45
SAE 110 Oil	140	150
Castor Oil	70	1,000
Ketchup	70	3,000
Asphalt	100	3,000,000
Asphalt	300	1,000
Molasses, "A"	70	3,000
Molasses, "B"	70	20,000
Molasses, "C"	70	80,000
Honey	70	5,000
Mayonnaise	70	40,000
White Glue	70	2,500
Caulking Cmpd.	70	75,000
Glycerine	70	1,500